

US 5759563
5780044
5744153 PCT




WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61K 9/22, 47/48		A1	(11) International Publication Number: WO 95/27481
			(43) International Publication Date: 19 October 1995 (19.10.95)
(21) International Application Number: PCT/US95/03792		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TT, UA, UG, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG).	
(22) International Filing Date: 27 March 1995 (27.03.95)			
(30) Priority Data: 08/225,140 8 April 1994 (08.04.94) US			
(71) Applicant: ATRIX LABORATORIES, INC. [US/US]; 2579 Midpoint Drive, Fort Collins, CO 80525 (US).		Published With international search report.	
(72) Inventors: YEWEY, Gerald, L.; 503 Dennison Court, Fort Collins, CO 80526 (US). KRINICK, Nancy, L.; 723 Stover Street, Fort Collins, CO 80524 (US). DUNN, Richard, L.; 5021 Kitchell Way, Fort Collins, CO 80524 (US). RADOMSKY, Michael, L.; Apartment 10, 2005 Rock Street, Mountain View, CA 94043 (US). BROUWER, Gerbrand; 112 Chester Street, Menlo Park, CA 94025 (US). TIPTON, Arthur, J.; 686 Summit Point, Birmingham, AL 35226 (US).			
(74) Agent: BRUESS, Steven, C.; Merchant, Gould, Smith, Edell, Welter & Schmidt, 3100 Norwest Center, 90 South Seventh Street, Minneapolis, MN 55402 (US).			

(54) Title: LIQUID DELIVERY COMPOSITIONS.



(57) Abstract

Improved biocompatible liquid delivery compositions, which are useful for the formation of sustained release delivery systems for active agents, are provided. The compositions include liquid formulations of a biocompatible polymer or prepolymer in combination with a controlled release component. The controlled release component includes an active agent. These compositions may be introduced into the body of a subject in liquid form which then solidify or cure *in situ* to form a controlled release implant or a film dressing. The liquid delivery compositions may also be employed *ex situ* to produce a controlled release implant. Methods of forming a controlled release implant and employing the liquid formulations in the treatment of a subject are also provided.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

LIQUID DELIVERY COMPOSITIONS

Background of the Invention

5 A variety of approaches have been developed to permit the continuous, sustained release of drugs into a subject. These controlled release systems are designed to protect the drug from the environment prior to delivery while permitting the controlled release of the
10 drug to a targeted area. All of the currently available approaches, however, suffer from one or more disadvantages or limitations.

A number of conventional controlled release systems are based on microstructures, such as
15 lipospheres, liposomes, microcapsules, microparticles, and nanoparticles. The microstructures are typically introduced into the body of a subject in the form of a dispersion. While microstructure dispersions are useful for many applications, these systems cannot be used to
20 form a continuous barrier film or a solid implant with the structural integrity required for prosthetic applications. In addition, when inserted into a body cavity where there is considerable fluid flow, e.g., the mouth or eye, microstructures may be poorly retained due
25 to their small size and discontinuous nature. Another limitation of such microstructure-based systems is the lack of reversibility of introduction without extensive and complex surgical intervention. If complications arise after their introduction, systems based on
30 microstructures are considerably more difficult to remove from the body of a subject than a solid implant.

Conventional controlled delivery systems may also be prepared as macrostructures. An active agent, such as a drug, may be blended with a polymer. The
35 blend is then shaped into a specific form such as a cylinder, disc or fiber for implantation. Alternatively, a solid porous implant, which is formed from a biodegradable polymer, may serve as a container to hold one of the controlled release microsystems

described above in place in a subject. With either of these solid implant approaches, the drug delivery system is typically inserted into the body through an incision. These incisions are often larger than desired and can
5 lead to a reluctance on the part of the subject to accept such a treatment.

Both microstructures and macrostructures of conventional controlled release systems may be prepared from polymer-drug conjugates. As such they have the
10 same disadvantages as those described earlier for similar structures of other conventional controlled release systems. In addition, polymer-drug conjugates may be prepared from water-soluble polymers so that they cannot be retrieved if needed. Because polymer-drug
15 conjugates afford a variety of drug release mechanisms, such as hydrolysis, enzymatic cleavage, or photocleavage and permit a greater degree of control over release rates, it would be desirable if they could be prepared without the above disadvantages.

20 The disadvantages of the systems described above have been overcome to some extent by the development of drug delivery systems which can be administered as a liquid (e.g., via syringe) and are subsequently transformed *in situ* into a solid implant.
25 For example, liquid polymeric compositions for use as biodegradable controlled release delivery systems are described in U.S. Patent Nos. 4,938,763, 5,278,201 and 5,278,202. These compositions may be administered to the body in a liquid state. Once in the body, the
30 composition coagulates or cures to form a solid. One such polymeric composition includes a nonreactive thermoplastic polymer or copolymer dissolved in a water-soluble solvent. This polymeric solution is introduced into the body, e.g., via syringe, where it "sets up" or
35 solidifies upon dissipation or diffusion of the solvent into surrounding body fluids. The other injectable polymeric composition is based on a thermoset system of

prepolymers that can be cured *in situ*. This polymeric system includes reactive liquid oligomeric prepolymers which cure by cross linking to form solids, usually with the aid of a curing agent.

5 These injectable liquid polymeric systems have a number of distinct advantages. While avoiding the requirement for an incision, the liquid delivery systems permit the formation of an implant with sufficient structural integrity to be used as prosthetic devices or
10 as a continuous barrier film. Because a solid implant is formed, these liquid systems also avoid the problems of dissipation observed with microstructure dispersions in those portions of the body which experience considerable fluid flow. Despite these advantages, the
15 liquid delivery systems currently available for forming implants *in situ* lack certain desirable characteristics.

 When a liquid delivery system including a biodegradable polymer and an active agent dissolved in a water-soluble solvent, comes into contact with an
20 aqueous medium such as a body fluid, the solvent dissipates or diffuses into the aqueous medium. As the polymer precipitates or coagulates to form a solid matrix, the active agent is trapped or encapsulated throughout the polymeric matrix. The release of the
25 active agent then follows the general rules for the dissolution or diffusion of a drug from within a polymeric matrix. The formation of the solid matrix from the liquid delivery system is, however, not instantaneous but typically occurs over a period of
30 several hours. During this initial period, the rate of diffusion of the active agent may be much more rapid than the rate of release that occurs from the subsequently formed solid matrix. This initial burst affect (i.e. the amount of active agent released in the
35 first 24 hours) may result in the loss or release of a large amount of the active agent prior to the formation of the solid matrix. If the active agent is

particularly toxic, this initial release or burst is likely to lead to toxic side effects and may cause damage to the adjacent tissues.

The development of liquid delivery systems that would allow the *in situ* formation of an implant while reducing or eliminating the initial burst effect would represent a significant advancement. Such delivery systems would permit higher concentrations of an active agent to be safely incorporated into an implant. The efficiency of such systems would also be improved, since a much greater percentage of the active agent would remain in the implant for sustained release and not be lost during the initial burst. Optimally, the liquid delivery system would afford a number of modes of controlling the release of an active agent from the system. These advantages would extend the application of such treatments as well as reducing the possibility of toxic side effects. There is, therefore, a continuing need for controlled release systems which can be introduced in liquid form to form a solid implant *in situ* and which will facilitate the sustained release of an active agent in a subject's body without creating an initial burst of active agent.

25

Summary of the Invention

The present invention provides liquid compositions which are useful for the delivery of active agents *in vivo* and permit the initial burst of active agent to be controlled more effectively than previously possible. This can be done, for example, by incorporating the active agent into a controlled release component and combining the controlled release component with the liquid polymer systems described in U.S. Patent Nos. 4,938,763, 5,278,201 and 5,278,202. The controlled release component may include a microstructure (e.g. a microcapsule) or macrostructure (e.g. a film or fiber) controlled release system, a molecular controlled

release system (e.g. a polymer/drug conjugate) or combinations thereof. The resulting liquid delivery compositions may include either liquid or solution formulations of a biocompatible prepolymer, polymer or
5 copolymer in combination with the controlled release component. These liquid delivery compositions may be introduced into the body of a subject in liquid form. The liquid composition then solidifies or cures *in situ* to form a controlled release implant.

10 The formulation employed to form the controlled release implant *in situ* may be a liquid delivery composition which includes a biocompatible polymer which is substantially insoluble in aqueous medium, an organic solvent which is miscible or
15 dispersible in aqueous medium, and the controlled release component. The biocompatible polymer is substantially dissolved in the organic solvent. The controlled release component may be either dissolved, dispersed or entrained in the polymer/solvent solution.
20 In a preferred embodiment, the biocompatible polymer is biodegradable and/or bioerodable.

The liquid delivery composition may be used to form a solid controlled release implant on either the inside or outside of the subject's body. In one
25 embodiment of the invention, the liquid delivery composition is introduced to an implant site in the subject where the composition solidifies to form the controlled release implant upon contact with a body fluid. In another embodiment of the invention, a solid
30 implant (may) be formed outside the subject by contacting the liquid composition with an aqueous medium. The solid implant may then be inserted into an implant site in the subject.

In yet another embodiment of the present
35 invention, the liquid delivery composition may be used to form a film dressing on a tissue of a subject. An amount (effective to form a film dressing) of the liquid

composition is dispensed onto the tissue, such as by spraying, painting or squirting, and the film dressing is formed on the tissue by contacting the liquid delivery composition with an aqueous medium.

5 The invention also includes a method for treating a subject with an active agent by administering the liquid delivery composition to an implant site in a subject to form a solid controlled release implant in situ. The treatment of a subject with the active agent
10 may also be carried out by inserting into the subject a solid sustained release implant formed outside the subject by contacting the liquid delivery composition with an aqueous medium. The present invention also encompasses a method which includes treating a subject's
15 tissue (e.g. injured tissue) by administering an effective amount of the liquid delivery composition to form a film dressing on the tissue.

 In another embodiment of the invention, the controlled release component incorporating the active
20 agent may also be introduced into a subject's body as part of a liquid delivery composition which includes a liquid, biocompatible prepolymer. The liquid prepolymer has at least one polymerizable ethylenically unsaturated group (e.g., an acrylic-ester-terminated prepolymer).
25 If a curing agent is employed, the curing agent is typically added to the composition just prior to use. The prepolymer remains a liquid for a short period after the introduction of the curing agent. During this period the liquid delivery composition may be introduced
30 into a body, e.g., via syringe. The mixture then solidifies in situ to form a solid implant. Other embodiments of the liquid delivery system may also include a pore-forming agent or an organic solvent which is miscible or dispersible in aqueous medium in addition
35 to the prepolymer and controlled release component. Alternatively, the pore-forming agent or the organic solvent may be added to the liquid prepolymer

composition together with or just after the addition of the curing agent. When a liquid delivery composition including the pore-forming agent or the organic solvent in combination with the prepolymer is employed, the
5 implant which is formed includes a solid microporous polymer matrix having the controlled release component embedded therewithin.

Another embodiment of the present invention is directed to a method of treating a subject with the active agent which includes introducing the liquid prepolymer composition into the subject. Yet another embodiment of the invention provides for treating an injured tissue of a subject including administering on the injured tissue an effective amount of the liquid prepolymer composition to form a film dressing.

Another method to provide liquid compositions which are useful for the delivery of active agents in vivo and permit the initial burst of active agent to be controlled more effectively than previously possible is to conjugate the active agent with a water-insoluble biocompatible polymer and dissolve the resultant polymer-active agent conjugate in a biocompatible solvent to form a liquid polymer system similar to that described in U.S. Patent Nos. 4,938,763, 5,278,201 and 5,278,202. The water-insoluble biocompatible polymers may be those described in the above patents or related copolymers. In addition, the liquid polymer system may also include a water-insoluble biocompatible polymer which is not conjugated to the active agent. In one embodiment of the invention, these liquid compositions may be introduced into the body of a subject in liquid form. The liquid composition then solidifies or coagulates in situ to form a controlled release implant where the active agent is conjugated to the solid matrix polymer. In another embodiment of the invention, a solid implant may be formed outside the subject by contacting the liquid composition with an aqueous

medium. The solid implant may then be inserted into an implant site in the subject. In yet, another embodiment of the present invention, the liquid delivery composition may be used to form a film dressing on a tissue of a subject.

Brief Description of the Drawings

Figure 1 shows the cumulative amount of naltrexone released from formulations in 75/25 poly(D,L-lactide-co-glycolide) (PLG) dissolved in NMP. The formulations included either free naltrexone or microparticles prepared by melt fusion of naltrexone and poly(D,L-lactide) (PLA). Each of the formulations contained 5.0% w/w naltrexone (on a free drug basis).

Figure 2 shows the cumulative amount of an antipsychotic drug (APD) released from formulations in 75/25 PLG dissolved in NMP. The formulations included either free APD or APD encapsulated with high molecular weight poly(vinyl pyrrolidinone) ("PVP"). Each of the formulations contained 5.0% w/w APD (on a free drug basis).

Figure 3 shows the cumulative amount of chlorin e_6 released from formulations in 75/25 PLG dissolved in DMSO. The formulations included either free chlorin e_6 and chlorin e_6 covalently bound to an (N-2-hydroxypropyl)-methacrylamide)/N-methacryloylglycine copolymer. Each of the formulations contained 0.5% w/w chlorin e_6 (on a free drug basis).

Detailed Description of the Invention

The present invention provides biocompatible liquid delivery compositions which may be used to form solid structures which permit an active agent to be delivered in a sustained, controlled manner. The compositions are typically administered in liquid form. After insertion, the compositions solidify or cure ("set up") to form a solid or gelatinous matrix ("implant"),

which is substantially insoluble in aqueous media, such as body fluids. Based on the relative partitioning properties of the active agent in a given formulation, an initial release of a comparatively large amount of the active agent may be observed. In some instances this initial release may not be problematic, e.g., the active agent may be a drug with a large therapeutic window. In other cases, however, the initial release may cause damage to adjacent tissues or lead to toxic side effects.

Liquid polymer system with controlled release component.

The initial burst may be decreased or avoided by modifying the physical state of the active agent, e.g., incorporating the active agent into a controlled release component which is then dissolved, dispersed or entrained in the liquid delivery composition. For example, the controlled release component may include microstructures, macrostructures, conjugates, complexes or low water-solubility salts. In principle, the additional time required to release the active agent from the controlled release component will enable the formulation to solidify into a solid implant without the initial loss of a substantial amount of the active agent. Thus, the present compositions are useful for the delivery of active agents in vivo and permit the initial burst of active agent to be controlled more effectively than previously possible.

Examples of suitable controlled release components include microstructures such as microparticles, nanoparticles, cyclodextrins, microcapsules, micelles and liposomes. The controlled release component may also include macrostructures such as fibers, rods, films, discs or cylinders. Suitable controlled release components also include low water-solubility salts of the active agent and complexes or conjugates in which the active agent is operatively

associated with a carrier molecule. Further included within the definition of the controlled release component are combinations of the above approaches. For example, the controlled release component may be a
5 microstructure, such as a microcapsule, which includes the active agent as part of a complex, conjugate, or low water-solubility salt.

If the liquid delivery composition is to be introduced into the subject by injection, the size of
10 the microcapsules or microparticles is typically limited to no more than 500 microns, and preferably no more than 150 microns. Microstructures larger than 500 microns are difficult to deliver via syringe or rubber tube and may be uncomfortable or irritating to the surrounding
15 tissues. In other applications, the controlled release component may, however, include a macrostructure such as a fiber, a film or a larger polymer bead. These may be dispersed, entrained or associated with the liquid portion of the liquid delivery composition such that the
20 composition solidifies to form a matrix with the macrostructure embedded therein. Alternatively, the liquid portion may act as an adhesive to hold the macrostructure in place at an implant site in the subject's body. The macrostructures are larger than 500
25 microns. The upper limits on size of the macrostructures will depend on the particular application.

Once formed into a solid matrix, the resulting implant provides at least dual modes for controlling the
30 release of the active agent - a first mode based on the rate of release of the active agent from the controlled release component and a second mode based on the release from the implant matrix. The second mode is governed by the rate of biodegradation and/or bioerosion of the
35 implant material and may also be governed by diffusion where the implant is a microporous matrix. The rate of release from the controlled release component may also

be governed by the rate of biodegradation and/or bioerosion of a polymer matrix, e.g., where the controlled release component is a polymeric microparticle or microcapsule. The release rate may also depend on a variety of other processes, such as where the controlled release component includes a conjugate of a carrier molecule and the active agent. The rate of release of the active agent from the conjugate may also be governed by the rate of breakdown of the conjugate.

The choice of a particular controlled release component will depend on the physical characteristics of the active agent (e.g., solubility, stability, etc.) and the desired properties of the liquid composition and the resulting implant. The controlled release component may include one or more of a variety of materials. The controlled release component may include a polymer, e.g., as the matrix of a microparticle, as the coating of a microcapsule, or as the carrier molecule of an active agent conjugate. The controlled release component may also include a hydrophobic counterion, such as when the active agent is present as a low water solubility salt. The controlled release component may include combinations of the above, such as where the controlled release component includes an active agent-conjugate encapsulated within a polymer coating.

The controlled release component may include a plurality of microstructures such as microparticles, microcapsules or nanoparticles. The microparticles or microcapsules are typically between 1 and 500 microns in size, although smaller particles may be used (e.g., nanoparticles which range in size from 10 nanometers to 1000 nanometers). Microcapsules in this context are defined as reservoir systems in which a simple reservoir of material which includes the active agent is surrounded by a membrane shell. The reservoir may contain only the active agent or it may include other

materials such as a polymer matrix or a release rate modification agent. Alternatively, the reservoir may include the active agent incorporated as part of a conjugate, a complex or a low water solubility salt.

5 Microparticles are small monolithic entities in which the active agent is distributed throughout the particle matrix, typically in a random fashion. However, many practical formulations fall between these two definitions. For example, microcapsules may agglomerate

10 during the microencapsulation process. In other instances, the size of the active agent particles contained in a "microcapsule" system may be of the same order as the size of the microcapsules themselves. For the purposes of this invention the term "microstructure"

15 is defined to include microparticles, nanoparticles, microcapsules or any related intermediate forms. Various physical and chemical methods for preparing these microstructures have been developed and the technology is well established and well documented. See

20 for example Patrick V. Deasy, "Microencapsulation and Related Drug Processes," Marcel Dekker Inc., New York (1984). A variety of exemplary methods of preparing microcapsules and microparticles are known (see e.g., U.S. Patent Nos. 4,061,254, 4,818,542, 5,019,400 and

25 5,271,961; and Wakiyama et al., Chem. Pharm. Bull., 29, 3363-68 (1981)). Depending on the chemical and physical properties desired, a number of these methods may be used to prepare microcapsules or microparticles.

The microparticles may be in the form of

30 lipospheres. In this instance, the microparticles include a phospholipid and optionally, an inert solid material, such as a wax. Lipospheres are solid, water-insoluble microparticles which have a layer of the phospholipid embedded on their surface. The core of the

35 lipospheres contain either a solid active agent or an active agent that is dispersed in the inert solid material (see, e.g., U.S. Patent 5,188,837).

Liposomes containing the active agent typically are formed in an aqueous solution by one of a well-known methods (see e.g. U.S. Patent 5,049,386). The aqueous solution containing the liposomes may be
5 incorporated in the compositions of the present invention, for example by forming a water-in-oil emulsion of this solution in a liquid pre-polymer. After curing, a polymer matrix with the liposomes embedded therein is formed.

10 Nanoparticles are carriers for drugs or other active molecules which are prepared in the nanometer size range (10 nm - 1000 nm). Drugs can be incorporated into nanoparticles using colloidal coacervation of
15 polymers, absorption on the surface of solid colloidal polymeric carriers, coating of the particles by polymerization, polycondensation, or coacervation, solidifying spherical micelles under
nanocompartmentation by polymerization or polycondensation, and interfacial polymerization
20 techniques using electrocapillary emulsification.

For example, the nanoparticles may include nanospheres as described in Gref et al., Science, 263, 1600-1602 (1994). The nanospheres may be formed from
25 diblock polymers which have a lipophilic block and a hydrophilic block. The active agent is distributed throughout the nanosphere and is typically present as a molecular dispersion throughout the lipophilic core of the nanospheres. When present in the nanospheres at a high loading, however, a phase separation of the active
30 agent may occur leading to the formation of agglomerates or crystals of active agent.

The liquid delivery compositions may also include a number of macrostructures such as fibers, rods, films, discs or cylinders. These macrostructures
35 may consist of reservoir systems in which the active agent is surrounded by a membrane which controls the rate of release, or monolithic systems in which the

active agent is distributed throughout the macrostructure matrix.

The present liquid delivery compositions, offer the advantage of safe, sustained release of a
5 active agent without an initial burst effect. In another embodiment of the invention, this may be achieved by incorporating the active agent (e.g., a drug) in a controlled release component which includes a conjugate. Conjugates in this context are defined as a
10 controlled release component in which the active agent is covalently bonded to a carrier molecule. By covalently bonding the active agent to the carrier molecule, the solubility and transport properties of the active agent are altered. Preferably, the carrier
15 molecule has no biological activity of its own and is readily biodegraded. The carrier molecule is typically a polymer but may also be a smaller organic molecule. For instance, the active agent may be covalently bonded to a small molecule such as stearic acid through an ester
20 or amide linkage, thereby decreasing the water solubility of the active agent.

The polymers used to prepare drug conjugates may be water-soluble, e.g. polyethylene glycol, poly-L-aspartic acid, poly(glutamic acid), polylysine,
25 poly(malic acid), dextran, and copolymers of N-(2-hydroxypropyl)-methacrylamide (HPMA). The polymers employed to prepare drug conjugates may also include water-insoluble polymers such as polyglycolide, poly(DL-lactide) (PLA), polycaprolactone (PCL), polyorthoesters,
30 polycarbonates, polyamides, polyanhydrides, polyurethanes, polyesteramides, polyphosphazenes, polyhydroxybutyrates, polyhydroxyvalerates, polyalkylene oxalates, and copolymers, terpolymers, or combinations or mixtures thereof. Some polymers or copolymers may be
35 either water-soluble or water-insoluble depending upon their molecular weight and ratio of monomers incorporated into the copolymer, e.g. poly(lactide-co-

lysine) and poly(lactide-co-malolactonic acid). In order for the drug to be conjugated to these polymers, they must have reactive groups such as hydroxyl, carboxyl, or amine groups. These reactive groups may be
5 either at the terminal ends of the polymers or on side-chains to the main polymer structure. If the reactive groups are terminal groups, the molecular weight of the polymer may need to be relatively low to have enough end groups to achieve the desired drug loading. There are a
10 number of ways to attach a drug to polymers with reactive groups. These include the formation of activated ester groups such as p-nitrophenyl esters, hydroxysuccinimide esters, and the use of dicyclohexyl carbodiimide (DCC). The polymer-drug conjugates may be
15 incorporated into the liquid polymer compositions as either microstructures or macrostructures. They also may be simply dissolved or dispersed in the liquid polymer compositions.

A variety of polymers such as poly(amino
20 acids), poly(amino acid esters), poly(carboxylic acids), poly(hydroxycarboxylic acids), polyorthoesters, polyphosphazenes, polyalkylene glycols and related copolymers have been employed in the preparation of polymer/drug conjugates. For example, poly(amino acids)
25 such as poly-L-aspartic acid, poly(lysine), and poly(glutamic acid) have been utilized in the preparation of polymer/drug conjugates. Related copolymers such as poly(lactic acid-co-lysine) (PLA/Lys) and a poly(ethylene glycol)-poly(aspartic acid) block
30 copolymer have also been employed. Other polymers which are suitable for use in the preparation of polymer/drug conjugates include dextran and copolymers of N-(2-hydroxypropyl)-methacrylamide (HPMA copolymers). The
35 polymers used to prepare drug conjugates may be water-soluble, e.g., polyethylene glycol poly-L-aspartic acid, and poly(lysine), or alternatively may be a water-insoluble polymer such as poly(lactide-co-glycolide)

(PLG). Some of the copolymers utilized, e.g., PLA/Lys, may be either water-soluble or water-insoluble depending on the ratio of monomers incorporated into the copolymer. Other examples of thermoplastic polymers which may be employed as the carrier molecule include poly(glycolide), poly(D,L-lactide) (PLA), poly(caprolactone) (PLC) and copolymers of malolactonic acid and D,L-lactide (PLA/MLA).

The liquid delivery composition may consist solely of an organic solvent and a conjugate having the active agent covalently bound to a thermoplastic polymer which is substantially insoluble in aqueous medium, e.g. a low molecular weight PLA or PLG. Alternatively, the composition may include the thermoplastic polymer in unbound form as well as bound to the active agent.

In another embodiment of the present invention, the controlled release component may include a complex in which a carrier molecule is operatively associated with the active agent. The complex may also include a metal cation operatively associated with the active agent and the carrier molecule. For example, the complex may include a biodegradable polymer with carboxyl groups. The carboxyl groups on the polymer may form a coordination complex with a drug and a metal such as zinc, magnesium or calcium. These complexes may break down on contact with water. However, the fact that the drug is part of a complex may prevent the drug from diffusing out of the implant as rapidly as the corresponding free drug.

The controlled release component may include a salt, such as a low water solubility salt of the active agent. For purposes of this invention, the term "low water solubility salt" is defined as a salt which has a solubility of no more than 25 mg/l (25 ppm). The solubility of the low water solubility salt is hereby defined as the amount of salt which can be measured in solution when the salt is dispersed or stirred for 4

hours in distilled water at a temperature of no more than 40°C. The low water solubility salt typically includes a non-toxic, water-insoluble carboxylate anion as a counterion for the active agent (e.g., the anionic form of pamoic acid, tannic acid or stearic acid). This method of reducing the initial burst effect is particularly useful where the active agent is a water soluble bioactive agent such as a peptide (see e.g., U.S. Patent 5,192,741). The low water solubility salt of the active agent may be dispersed in the liquid delivery compositions of the present invention. Alternatively, the low water solubility salt may be microencapsulated or dispersed in the polymeric matrix of a microparticle prior to incorporation into the liquid delivery composition.

The present controlled release components may be prepared from polymers or materials which are either soluble or insoluble in the final liquid delivery composition, i.e., soluble or insoluble in the organic solvent or liquid prepolymer. The polymer or materials used in the preparation is insoluble, the compositions may be prepared and stored as dispersions, e.g., of microparticles or microcapsules. Where the polymer or material is soluble in the bulk liquid composition, the controlled release component may be added and mixed into the composition just prior to its use. The exact time window during which such compositions may be used will depend on the rate of dissolution of the polymer or material in the particular composition. For example, if the polymer or material of the controlled release component is only sparingly soluble in the bulk composition, it may be possible to store the composition as a dispersion or mixture for a limited period of time. Alternatively, if the controlled release component is an active agent conjugate which is soluble in the bulk liquid composition, all of the components of the

composition may be blended together to form the liquid composition well in advance of its use.

In one embodiment of the invention, the controlled release component may be dissolved, dispersed or entrained in a solution formulation of a polymer or copolymer to form the liquid delivery composition. The liquid delivery composition typically includes a biodegradable and/or bioerodable, biocompatible polymer or copolymer dissolved in a nontoxic organic solvent. The solvent is miscible or dispersible in aqueous medium, such as body fluids. This liquid composition may be injected or inserted into an implant site of a subject's body. Upon contact with body fluids in the adjacent tissues, the liquid composition solidifies *in situ* to form a controlled release implant. The controlled release implant is a solid polymer matrix having the controlled release component embedded therewithin.

Alternatively, the controlled release component may be dissolved or dispersed in a liquid formulation of a prepolymer to form the liquid delivery composition. After injection or insertion into an implant site, the prepolymer is cured to form a solid polymeric matrix having the controlled release component embedded there within. The curing step may be carried out with the aid of a curing agent or by other known methods, e.g., by exposing the prepolymer to electromagnetic radiation. If a curing agent is employed, a mixture which includes the prepolymer and the controlled release component is formed. The curing agent is typically added to this mixture to form a liquid prepolymer preparation just prior to injection.

In one embodiment of the present invention, the controlled release component, including the active agent, may be introduced into the body of a subject as part of a liquid composition. The liquid composition includes a biocompatible polymer which is substantially

insoluble in aqueous medium, in combination with an organic solvent, and the controlled release component. The organic solvent is miscible or dispersible in aqueous medium. Preferably, the biocompatible polymer is biodegradable and/or bioerodable. The polymer is typically a thermoplastic polymer such as a polylactide, a polycaprolactone or a polyglycolide. The active agent may be a bioactive agent or a diagnostic agent. As used herein, the term "bioactive agent" means a drug, medicament, or some other substance capable of producing an effect on a body. As used herein, the term "diagnostic agent" means a substance, such as an imaging agent, which permits the detection or monitoring of a physiological condition or function. The liquid delivery composition may be injected or inserted into an implant site of the body of the subject. On contact with aqueous medium, such as body fluids in the adjacent tissues, the liquid delivery composition solidifies in situ to form a controlled release implant. The organic solvent of the liquid composition dissipates into surrounding tissue fluids and the polymer coagulates to form a solid implant. The implant is a solid polymer matrix having the controlled release component embedded therewithin. The implant permits the controlled delivery of active agents such as drugs, medicaments, diagnostic agents and the like.

The liquid composition may also be employed to form an implant precursor outside the body. The structure of the implant precursor is composed of an outer sack and a liquid filling. After introduction of the implant precursor into the body of the subject, contact with a body fluid results in the *in situ* formation of the controlled release implant. The implant precursor includes a mixture of a biocompatible polymer which is substantially insoluble in aqueous medium, the controlled release component which includes

the active agent, and an organic solvent which is miscible or dispersible in aqueous medium.

As used herein, the term "implant site" is meant to include a site, in or on which the controlled release implant is to be formed or applied, as for example, a soft tissue such as muscle or fat, or a hard tissue such as bone. Examples of implant sites include a tissue defect such as a tissue regeneration site; a void space such as a periodontal pocket, surgical incision or other formed pocket or cavity; a natural cavity such as the oral, vaginal, rectal or nasal cavities, the cul-de-sac of the eye, and the like; and other sites into which the liquid delivery composition or implant precursor may be placed and formed into a solid implant.

The present liquid delivery composition may include a biocompatible polymer or copolymer in combination with a controlled release component and an organic solvent. As disclosed in U.S. Patent No. 4,938,763, the disclosure of which is incorporated by reference herein, the organic solvent is biocompatible and miscible or dispersible in aqueous medium. The liquid composition may optionally include a pore-forming agent and/or a physiologically acceptable rate modifying agent. The liquid composition and resulting implant precursor and/or solid implant are biocompatible in that neither the polymer, the solvent, the controlled release component nor the polymer matrix cause substantial tissue irritation or necrosis at the implant site.

The polymers or copolymers are substantially insoluble in aqueous medium, e.g., body fluids, and are biodegradable and bioerodable and/or bioabsorbable within the body of an animal. The term "biodegradable" means that the polymer and/or polymer matrix of the implant will degrade over time by the action of enzymes, by hydrolytic action and/or by other similar mechanisms in the human body. By "bioerodible," it is meant that

the implant matrix will erode or degrade over time due, at least in part, to contact with substances found in the surrounding tissue fluids, cellular action, and the like. By "bioabsorbable," it is meant that the polymer matrix will be broken down and absorbed within the human body, for example, by a cell, a tissue, and the like.

Thermoplastic polymers. Thermoplastic polymers useful in the liquid delivery composition include biocompatible polymers that are biodegradable and/or bioerodable and bioabsorbable, and soften when exposed to heat but return to their original state when cooled. The thermoplastic polymers are capable of substantially dissolving in an organic solvent. The thermoplastic polymers are also capable of coagulating or precipitating to form an outer membrane, and an inner core consisting of a solid microporous matrix upon the dissipation of the solvent component from the polymer solution, and the contact of the polymer with an aqueous medium.

Thermoplastic polymers that are suitable for use in the polymer solution generally include any having the foregoing characteristics. Examples are polylactides, polyglycolides, polycaprolactones, polyanhydrides, polyamides, polyurethanes, polyesteramides, polyorthoesters, polydioxanones, polyacetals, polyketals, polycarbonates, polyorthoesters, polyphosphazenes, polyhydroxybutyrates, polyhydroxyvalerates, polyalkylene oxalates, polyalkylene succinates, poly(amino acids), poly(methyl vinyl ether), poly(maleic anhydride), chitin, chitosan, and copolymers, terpolymers, or combinations or mixtures therein. Polylactides, polycaprolactones, polyglycolides and copolymers thereof are highly preferred thermoplastic polymers.

The thermoplastic polymer is combined with a suitable organic solvent to form a solution. The

solubility or miscibility of a polymer in a particular solvent will vary according to factors such as crystallinity, hydrophilicity, capacity for hydrogen-bonding, and molecular weight of the polymer.

- 5 Consequently, the molecular weight and the concentration of the polymer in the solvent are adjusted to achieve desired solubility. Preferably, the thermoplastic polymers have a low degree of crystallization, a low degree of hydrogen-bonding, low solubility in water, and
10 high solubility in organic solvents.

Solvents. Suitable solvents for use in the present liquid delivery composition are those which are biocompatible, pharmaceutically-acceptable, miscible
15 with the polymer ingredient and aqueous medium, and capable of diffusing into an aqueous medium, as for example, tissue fluids surrounding the implant site, such as blood serum, lymph, cerebral spinal fluid (CSF), saliva, and the like. In addition, the solvent is
20 preferably biocompatible. Typically, the solvent has a Hildebrand solubility parameter of from about 9 to about $13(\text{cal}/\text{cm}^3)^{1/2}$. The degree of polarity of the solvent should be effective to provide at least about 10% solubility in water, and to dissolve the polymer
25 component.

Solvents that are useful in the liquid delivery composition, include, for example, N-methyl-2-pyrrolidone; 2-pyrrolidone; aliphatic alcohols having from two to eight carbon atoms; propylene glycol;
30 glycerol; tetraglycol; glycerol formal; solketal; alkyl esters such as ethyl acetate, ethyl lactate, ethyl butyrate, dibutyl malonate, tributyl citrate, tri-n-hexyl acetylcitrate, diethyl succinate, diethyl glutarate, diethyl malonate, and triethyl citrate;
35 triacetin; tributyrin; diethyl carbonate; propylene carbonate; aliphatic ketones such as acetone and methyl ethyl ketone; dialkylamides such as dimethylacetamide

and dimethylformamide; cyclic alkyl amides such as caprolactam; dimethyl sulfoxide; dimethyl sulfone; decylmethylsulfoxide; oleic acid; aromatic amides such as N,N-diethyl-m-toluamide; 1-dodecylazacycloheptan-2-one, and 1,3-dimethyl-3,4,5,6-tetrahydro-2(1H)-pyrimidinone and the like. Preferred solvents according to the present invention include N-methyl-2-pyrrolidone (NMP), 2-pyrrolidone, ethyl lactate, dimethyl sulfoxide (DMSO), and propylene carbonate.

10 A mixture of solvents providing varying degrees of solubility for the polymer components may be used to increase the coagulation rate of polymers that exhibit a slow coagulation or setting rate. For example, the polymer may be combined with a solvent
15 mixture which includes a good solvent (i.e., a solvent in which the polymer is highly soluble) and a poor solvent (i.e., a solvent in which the polymer has a low degree of solubility) or a non-solvent (i.e., one in which the polymer is insolvent). Preferably, the
20 solvent mixture contains a poor solvent or non-solvent and an effective amount of a good solvent, in admixture such that the polymer will remain soluble while in solution but coagulate or precipitate upon dissipation of the solvents into a surrounding aqueous medium, e.g.,
25 tissue fluids at the implant site.

The concentration of polymer in the liquid composition will generally permit rapid and effective dissipation of the solvent and coagulation or precipitation of the polymer. This concentration may
30 range from about 0.01 gram of polymer/ml of solvent to an about saturated concentration, preferably from about 0.1 gram/ml to an about saturated concentration, and more preferably from about 0.2 gram/ml to an about 0.7 gram/ml.

35

Thermoset Polymers. An *in situ* forming biodegradable implant can also be constructed by cross-linking

appropriately functionalized biodegradable prepolymers. The liquid thermosetting systems of the present invention include the controlled release component and reactive, liquid prepolymers. The liquid prepolymers will cure *in situ* to form a solid matrix, usually with the aid of a curing catalyst. In general, any biocompatible oligomer which may be linked to a polymerizable functional group to form a biocompatible prepolymer may be utilized. Although any of the biodegradable thermoplastic polymers described herein may be used, the limiting criteria is that low molecular weight oligomers of these polymers must be liquids and must have at least one functional group which can be reacted with a derivatizing agent containing a polymerizable functional group. Suitable liquid prepolymers include oligomers having pendant hydroxyl groups which have been reacted with a derivatizing agent to form a prepolymer having at least one polymerizable ethylenically unsaturated group. For example, a hydroxy terminated low molecular weight polylactide can be reacted with acryloyl chloride to produce an polylactide oligomer end capped with an acrylic ester. The ethylenically unsaturated groups on the prepolymers may then be polymerized by the addition of a curing catalyst, such as a free radical initiator or by exposure to electromagnetic radiation.

Because the prepolymer will remain liquid for a short period of time after addition of a curing agent, a mixture of the liquid prepolymer with a controlled release component and a curing agent may be manipulated, e.g., placed into a syringe and injected into a subject's body. The mixture then forms an solid implant *in situ* obviating the need for an incision. As with systems based on the thermoplastic polymers, the rate of release of the active agent will be affected by the rates of diffusion of the agent out of the implant. In some instances, the rate of release will be governed by

the biodegradation and/or bioerosion of the polymeric matrix implant. In others, the rate of release will be governed by the rate of release of the active agent from the controlled release component.

5

Active Agent. The liquid delivery compositions of the present invention include an active agent, such as a bioactive agent or a diagnostic agent, either singly or in combination, such that the implant or film dressing will provide a delivery system for the active agent to adjacent or distant tissues and organs in the subject. Bioactive agents which may be used alone or in combination in the implant precursor and implant include, for example, a medicament, drug, or other suitable biologically-, physiologically-, or pharmaceutically-active substance which is capable of providing local or systemic biological, physiological or therapeutic effect in the body of an animal including a mammal, and of being released from the solid implant matrix into adjacent or surrounding tissue fluids. Diagnostic agents which may be used include imaging agents, such as radiodiagnostic agents.

The active agent may be soluble in the polymer solution to form a homogeneous mixture, or insoluble in the polymer solution to form a suspension or dispersion. Upon implantation, the active agent preferably becomes embedded within the implant matrix. As the matrix degrades over time, the active agent is released from the matrix into the adjacent tissue fluids, preferably at a controlled rate. The release of the active agent from the matrix may be varied, for example, by the solubility of the active agent in an aqueous medium, the distribution of the agent within the matrix, the size, shape, porosity, solubility and biodegradability of the implant matrix, and the like.

The liquid delivery composition includes the bioactive agent in an amount effective to provide the

desired level of biological, physiological, pharmacological and/or therapeutic effect in the animal. There is generally no critical upper limit on the amount of the bioactive agent included in the liquid delivery
5 composition other than that dictated by the pharmacological properties of the particular bioactive agent. The lower limit of the amount of bioactive agent incorporated into the polymer solution will depend on the activity of the bioactive agent and the period of
10 time desired for treatment.

The bioactive agent may stimulate a biological or physiological activity with the animal. For example, the agent may act to enhance cell growth and tissue regeneration, function in birth control, cause nerve
15 stimulation or bone growth, and the like. Examples of useful bioactive agents include a substance, or metabolic precursor thereof, which is capable of promoting growth and survival of cells and tissues, or augmenting the functioning of cells, as for example, a
20 nerve growth promoting substance such as a ganglioside, a nerve growth factor, and the like; a hard or soft tissue growth promoting agent such as fibronectin (FN), human growth hormone (HGH), protein growth factor interleukin-1 (IL-1), and the like; a bone growth
25 promoting substance such as hydroxyapatite, tricalcium phosphate, and the like; and a substance useful in preventing infection at the implant site, as for example, an antiviral agent such as vidarabine or acyclovir, an antibacterial agent such as a penicillin
30 or tetracycline, an antiparasitic agent such as quinacrine or chloroquine.

Suitable bioactive agents for use in the invention also include anti-inflammatory agents such as hydrocortisone, prednisone and the like; anti-bacterial
35 agents such as penicillin, cephalosporins, bacitracin and the like; antiparasitic agents such as quinacrine, chloroquine and the like; antifungal agents such as

nystatin, gentamicin, and the like; antiviral agents such as acyclovir, ribarivin, interferons and the like; antineoplastic agents such as methotrexate, 5-fluorouracil, adriamycin, tumor-specific antibodies
5 conjugated to toxins, tumor necrosis factor, and the like; analgesic agents such as salicylic acid, acetaminophen, ibuprofen, flurbiprofen, morphine and the like; local anaesthetics such as lidocaine, bupivacaine, benzocaine and the like; vaccines such as hepatitis,
10 influenza, measles, rubella, tetanus, polio, rabies and the like; central nervous system agents such as a tranquilizer, B-adrenergic blocking agent, dopamine and the like; growth factors such as colony stimulating factor, platelet-derived growth factor, fibroblast
15 growth factor, transforming growth factor B, human growth hormone, bone morphogenetic protein, insulin-like growth factor and the like; hormones such as progesterone, follicle stimulating hormone, insulin, somatotropins and the like; antihistamines such as
20 diphenhydramine, chlorpheniramine and the like; cardiovascular agents such as digitalis, nitroglycerine, papaverine, streptokinase and the like; anti-ulcer agents such as cimetidine hydrochloride, isopropamide iodide, and the like; bronchodilators such as
25 metaproterenal sulfate, aminophylline and the like; vasodilators such as theophylline, niacin, minoxidil, and the like; and other like substances. The bioactive agent may also be an antihypertensive agent, an anticoagulant, an antispasmodic agent, or an
30 antipsychotic agent. For additional examples of bioactive agents that may be used in the present invention, see Applicants' corresponding U.S. Patent Application Serial No. 07/783,512, filed October 28, 1991, the disclosure of which is incorporated by
35 reference herein.

Accordingly, the formed implant may function as a delivery system of drugs, medicaments, other

biologically-active agents and diagnostic agents to tissues adjacent to or distant from the implant site. The active agent is incorporated into the controlled release component. In another embodiment of the invention, the active agent may also be incorporated directly into the polymeric matrix surrounding the controlled release component.

Liquid polymer-drug conjugates. The initial burst of drug from the liquid polymer systems described in U.S. Patent Nos. 4,938,763, 5,278,201 and 5,278,202 may also be decreased or avoided by conjugating the active agent directly to a water-insoluble biodegradable polymer and dissolving the resultant polymer-drug conjugate in a biocompatible solvent to form a liquid polymer system similar to those described in the above patents. The water-insoluble biocompatible polymers may be those described in these patents or related copolymers. Thus, polyglycolide, poly(D,L-lactide), polycaprolactone, polyorthoesters, polycarbonates, polyamides, polyanhydrides, polyurethanes, polyesteramides, polyphosphazenes, polyhydroxybutyrate, polyhydroxyvalerate, polyalkylene oxalates, and copolymers, terpolymers, or combinations or mixtures thereof with sufficiently low molecular weights to achieve the desired drug loading may be used. Also related copolymers or terpolymers such as poly(lactide-co-malolactonic acid), or combinations or mixtures of the polymers listed above with other polymers may be used to form a solid implant in which the active agent is directly conjugated to the polymer matrix.

The monomer ratios (D,L-lactide versus malolactonic acid) may be varied to obtain the balance of water insolubility and carboxyl group content desired for a particular application. In some instances, in order to obtain a copolymer with the properties desired, it may be advantageous to use other combinations of

monomers. For example, MLABE may also be polymerized with glycolide or caprolactone to yield, after removal of the benzyl protecting groups by hydrogenation, poly(glycolide-co-malolactonic acid) or
5 poly(caprolactone-co-malolactonic acid) respectively. Terpolymers such as poly(D,L-lactide/glycolide/malolactonic acid) may also be prepared by the same method.

- 10 Pore Structure. The implants formed using the present liquid delivery compositions preferably include a microporous inner core and a microporous outer skin. Typically, the pores of the inner core are substantially uniform and the skin of the solid implant is essentially
15 non-porous compared to the porous nature of the core. Preferably, the outer skin of the implant has pores with diameters significantly smaller in size than these pores in the inner core, e.g., the ratio of the average pore size in the core to the average pore size in the skin is
20 from about 2/1 to about 100/1, and preferably from about 2/1 to about 10/1.

Pores may be formed within the matrix of the implant by several means. The dissipation, dispersement or diffusion of the solvent out of the solidifying
25 polymer matrix into the adjacent tissue fluids may generate pores, including pore channels, in the polymer matrix. The dissipation of the solvent from the coagulating mass creates pores within the solid implant. The size of the pores of the solid implant are in the
30 range of about 1-1000 microns, preferably the size of pores of the skin layer are about 3-500 microns. The solid microporous implant has a porosity in the range of about 5-95%. Preferably the skin has a porosity of 5% to about 10% and the core has a porosity of about 40% to
35 about 60%.

Optionally, a pore-forming agent may be included in the polymer solution to generate additional pores in the

polymer matrix. This approach is described more fully in U.S. Serial No. 07/283,512, the disclosure of which is incorporated by reference herein. Suitable pore-forming agents include a sugar, a salt, a water-soluble polymer, and a water-insoluble substance that rapidly degrades to a water soluble substance.

Release Rate Modification Agents. The polymer solution may include a release rate modification agent to provide controlled, sustained release of a bioactive agent from the solid implant matrix. Suitable release rate modification agents include an ester of a monocarboxylic acid, an ester of a dicarboxylic acid, an ester of a tricarboxylic acid, a polyhydroxy alcohol, a fatty acid, a triester of glycerol, a sterol, an alcohol, and combinations thereof.

The present invention may be further described by reference to the following examples.

Example 1

Naltrexone/PLA Microparticles in PLG/NMP. A 1:1 melt/fusion mixture was prepared on a Teflon film by melting poly(D,L-lactide) (PLA; approx. 2,000 MW; Boehringer-Ingelheim; Resomer L104) and adding an equal quantity of naltrexone base. The melt was then allowed to cool to a fused solid. The fused solid was separated from the Teflon film and ground to a fine powder. A five percent w/w formulation of naltrexone was prepared by adding 30 mg of the melt/fused naltrexone/PLA powder to 300 mg of a solution of poly(D,L-lactide-co-glycolide) (PLG) in N-methylpyrrolidone (NMP). A 5% w/w control formulation of naltrexone was prepared by adding 15 mg of unprocessed naltrexone base to 300 mg of the PLG/NMP solution. The in-vitro release of naltrexone from each of the formulations was evaluated by adding a drop of formulation to a five ml aliquot of phosphate buffered saline solution (PBS) in a 10 ml vial. The

amount of naltrexone released was determined by storing the vial at 37°C and monitoring the absorbance at 280 nm as a function of time. The results (shown in Figure 1) indicate that the formulation which included the
5 microparticles of melt/fused naltrexone/PLA dispersed in the PLG/NMP solution significantly reduced the initial release of naltrexone (in comparison with the control solution of naltrexone in PLG/NMP).

10 Example 2

Ganirelix Microparticles in PLG/NMP. Ganirelix acetate (a GnRH antagonist suitable for treating endometriosis and prostate carcinoma) was incorporated in
microparticles of a solvent-insoluble, fast-biodegrading
15 polymer. This was done to decrease the solubility of ganirelix in the polymer/solvent formulation and to enhance the dispersing characteristics of the ganirelix acetate in this same formulation. Ganirelix acetate (6 gm) and poly(sebacic acid) (4 gm; "PSA") were mixed to
20 form a homogenous powder mixture. The powder mixture was melted on a hotplate at 80°C and mixed until the ganirelix acetate was homogeneously dispersed in the PSA melt. The ganirelix acetate/PSA melt was allowed to cool to room temperature to form a solid, which was then
25 ground in a Cryo-Mill for one minute to form a fine powder. The powder was sieved to collect the particles of less than 60 microns. A 50:50 solution of PLA in ethyl lactate was formed by dissolving an equal amount of PLA in ethyl lactate using a sonicator at 45°C. The
30 final formulation was prepared by adding 1.14 gm of the ganirelix acetate/PSA microparticles to 4 ml of the PLA/ethyl lactate solution. The resulting mixture, which was mixed well by shaking, could be administered through a 20 gauge needle. Due to the solubility of PSA
35 in ethyl lactate, this formulation was used within one hour of mixing. A relatively large burst effect is observed with formulations where ganirelix is simply

dissolved in the PLA/NMP solution (>10% during the first day after administration). This initial burst of ganirelix can cause local tissue irritation and is clinically unacceptable. In vitro and in vivo experiments demonstrated that the liquid composition with the ganirelix acetate/PSA microparticles eliminated the high initial release of ganirelix (<3% during the first day after administration).

10 Example 3

Porcine Somatotrophin Microcapsules in PLA/NMP. A PLA/NMP stock solution is prepared by dissolving PLA (2000 MW) in an equal amount of N-methylpyrrolidone (50:50 PLA/NMP). A liquid composition containing porcine somatotropin (PST) microcapsules is prepared by adding 0.2 g of microcapsules containing 41% by weight PST in a carboxymethyl cellulose matrix to 2.0 g of the PLA/NMP solution. A similar formulation is prepared by adding microcapsules containing PST in a gelatin matrix to the 50:50 PLA/NMP solution. The in vitro release of PST from these formulations is examined by dispensing the formulation (150-300 microliters) through a 20 gauge needle directly into 10 ml of phosphate buffered saline. The rate of release from the microcapsule formulations is significantly lower than the initial release of PST from the microcapsules alone.

Example 4

Microencapsulated Antipsychotic Drug in PLG/NMP.

Seventeen (17.0) grams of a benzisoazolpyrimidinone antipsychotic drug (APD) may be added to an aqueous solution (17.0 g polymer in 300 ml water) of a water-soluble, biodegradable polymer, poly(vinyl pyrrolidinone) ("PVP"; MW 100,000). The resulting preparation is a well dispersed suspension. This suspension is spray dried using a Büchi 190 mini spray drier with the following parameters: heating rate of 11,

aspiration rate of 20, compressed air pressure of 80 psi, air flow of 800 NL/hr, nozzle opening of 0.7 mm, inlet temperature of 167°C, and an outlet temperature of 103°C. After 75 min. of processing using the above conditions, 3.2 g of fine powder of APD encapsulated in PVP is obtained. A 5% w/w formulation of APD in dispersed in polymer solution may be prepared by adding 27 mg of the PVP-encapsulated particles to a solution of poly(D,L-lactide-co-glycolide) (60% 75/25 PLG (0.11)) in NMP. A control formulation was prepared by adding untreated APD (13.5 mg) to the same 60% PLG/NMP solution. The in-vitro release of APD from these formulations may be evaluated by adding a drop of the respective formulations to 5.0 ml aliquots of buffer solution (in 10 ml vials) and storing at 37°C. The absorbance is monitored at 280 nm as a function of time. The results indicate that coating the solid APD particles with a high molecular weight water soluble polymer reduces the initial release of APD (see Figure 2).

Example 5

Polymer-Bound Chlorin e₆ in PLG/DMSO. A conjugate of chlorin e₆ covalently bound to an N-(2-hydroxypropyl)-methacrylamide/N-methacryloylglycine copolymer (HPMA copolymer) containing glycy side chains was prepared according to the procedures described in Krinick, Ph.D. Dissertation: Combination Polymeric Drugs as Anticancer Agents, University of Utah (1992). The conjugate contained 11 wt.% chlorin e₆ and 89 wt.% HMPA copolymer. The chlorin e₆ was bound to the HPMA copolymer through the carboxyl groups of the pendant glycine residues. Two formulations were prepared, each containing 0.5 wt.% chlorin e₆ (on a free drug basis). One of the formulations contained 53 wt.% PLG (iv=0.11 dl/g), 46.5 wt.% DMSO and 0.5 wt.% free chlorin e₆. The second formulation 51 wt.% PLG, 44.75 wt.% DMSO and 4.25 wt.%

of the chlorin e_6 /HMPA copolymer conjugate. Drops of the two formulations were precipitated into 5 ml of phosphate buffered saline and the samples were placed on an environmental shaker at 37°C. The concentration of chlorin e_6 in the solution was monitored as a function of time using UV/visible spectroscopy ($\lambda_{\max} = 650$ nm). The cumulative percentage of drug released is shown in Figure 3. The results indicated that chlorin e_6 is released much more slowly from the formulation which contains the chlorin e_6 /HMPA copolymer conjugate. In addition, no burst effect was observed from the chlorin e_6 /HMPA copolymer conjugate formulation.

Example 6

PLA/MLA-p-doxorubicin in PLG/NMP. A water-soluble copolymer of D,L-lactide with malolactonic acid (PLA/MLA) may be prepared by initially copolymerizing D,L-lactide with malolactonic acid monobenzyl ester (MLABE). The benzyl protecting groups may be removed from the resultant copolymer by hydrogenation to yield a copolymer (PLA/MLA) with free carboxyl side chain groups. The free carboxyl groups may be reacted with dicyclohexylcarbodiimide and p-nitrophenol to yield a PLA/MLA copolymer with pendant p-nitrophenol ester groups. Doxorubicin may be attached to the PLA/MLA copolymer via an aminolysis reaction to yield a PLA/MLA-p-doxorubicin copolymer.

Sufficient PLA/MLA-p-doxorubicin may be added to a 60:40 PLG/NMP stock solution to form a liquid composition having 2.0% by weight doxorubicin (on a free doxorubicin basis). A control formulation of free doxorubicin may be prepared by adding 20mg of doxorubicin to 980mg of the 60:40 PLG/NMP stock solution. The in vitro release of doxorubicin from each of the formulations may be evaluated by adding a drop of formulation to a five ml aliquot of phosphate buffered saline solution (PBS) in a 10 ml vial. The free

doxorubicin formulation may show a substantial initial burst of the drug. Essentially no doxorubicin may be released over a period of 3 days from a sample which includes the PLA/MLA-p-doxorubicin. The in vitro
5 determination may be repeated by adding a drop of formulation to a five ml aliquot of rabbit peritoneal fluid in a 10 ml vial. The free doxorubicin formulation may show a substantial initial burst of doxorubicin. The PLA/MLA-p-doxorubicin containing composition may
10 show no burst and the rate of doxorubicin release may be much lower than the rate observed for the free doxorubicin formulation.

Example 7

15 PLG-t-Doxorubicin in PLG/NMP. Low molecular weight poly(D,L-lactide-co-glycolide) (PLG) with terminal carboxyl groups may be reacted with dicyclohexylcarbodiimide and p-nitrophenol to yield a PLG copolymer with terminal p-nitrophenol ester groups.
20 Doxorubicin may then be reacted with the p-nitrophenol ester groups to give a PLG copolymer with doxorubicin attached to the terminal carboxyl groups of the copolymer (PLG-t-doxorubicin).

The PLG-t-doxorubicin conjugate may then be
25 added to 60:40 PLG/NMP stock solution to form a liquid composition having 2.0% by weight doxorubicin (on a free doxorubicin basis). The rate of release of doxorubicin in PBS and rabbit peritoneal fluid may be determined using standard methods. As is observed with the PLA/MA-
30 p-doxorubicin composition, essentially no doxorubicin may be released over a period of 3 days from the addition of the sample which includes the PLG-t-doxorubicin to PBS. No burst effect may be effect may be observed with the addition of a drop of the PLG-t-
35 doxorubicin composition to rabbit peritoneal fluid. Once again, the rate of doxorubicin release into rabbit peritoneal fluid from the PLG-t-doxorubicin composition

may be much lower than the rate observed for the free doxorubicin formulation.

5 All publications and patent applications in
this specification are indicative of the level of
ordinary skill in the art to which this invention
pertains. All publications and patent applications
cited herein are incorporated by reference to the same
extent as if each individual publication or patent
10 application was specifically and individually
incorporated by reference.

The invention has been described with
reference to various specific and preferred embodiments
and techniques. However, it should be understood that
15 many variations and modifications may be made while
remaining within the spirit and scope of the invention.

WHAT IS CLAIMED IS:

1. A liquid delivery composition suitable for the formation of a controlled release implant, the composition comprising:
 - a) a biocompatible, thermoplastic polymer which is substantially insoluble in an aqueous medium;
 - b) a biocompatible organic solvent which is miscible or dispersible in an aqueous medium; and
 - c) a controlled release component which includes an active agent.
2. A liquid delivery composition suitable for the formation of a controlled release implant, the composition comprising:
 - a) an active agent/polymer conjugate in which the active agent is covalently bonded to a first biocompatible, thermoplastic polymer which is substantially insoluble in an aqueous medium; and
 - b) a biocompatible organic solvent which is miscible or dispersible in an aqueous medium.
3. The liquid delivery composition of claim 2, further comprising a second biocompatible, polymer which is substantially insoluble in an aqueous medium.
4. The liquid delivery composition of claims 1 or 2, wherein the composition, upon contact with an aqueous medium, is capable of forming a solid, microporous matrix having a core surrounded by a skin, the skin having pores with a substantially smaller diameter than pores of the core.
5. The liquid delivery composition of claim 4, wherein the skin has a porosity of about 5% to about 10%, and the core has a porosity of about 40% to about 60%.

6. The liquid delivery composition of claims 1 or 2, wherein the liquid composition has a viscosity which effectively allows for aerosolization of the composition.

7. A polymer system suitable for use as a controlled release implant, comprising:

a) a solid microporous matrix of a biocompatible polymer, the polymer being substantially insoluble in an aqueous medium; and

b) a controlled release component which includes an active agent, and is embedded within the microporous matrix;

wherein the matrix is prepared by contact between an aqueous medium and the liquid delivery composition of claims 1 or 2.

8. A biodegradable microporous film dressing formed from the liquid delivery composition of claims 1 or 2.

9. A controlled release implant precursor for implantation in a subject, formed from the liquid delivery composition of claims 1 or 2; wherein the implant precursor has a structure composed of an outer sack and a liquid filling.

10. Any of claims 1, 2, 7, 8 or 9, wherein the thermoplastic polymer is selected from the group consisting of polylactides, polyglycolides, polycaprolactones, polyanhydrides, polyamides, polyurethanes, polyesteramides, polyorthoesters, polydioxanones, polyacetals, polyketals, polycarbonates, polyorthoesters, polyphosphazenes, polyhydroxybutyrates, polyhydroxyvalerates, polyalkylene oxalates, polyalkylene succinates, poly(malic acid), poly(amino acids), poly(methyl vinyl ether), poly(maleic

anhydride), chitin, chitosan, and copolymers, terpolymers, and mixtures thereof.

11. Any of claims 1, 2, 7, 8 or 9, wherein the thermoplastic polymer is selected from the group consisting of polyglycolide, poly(D,L-lactide), polycaprolactone, polyorthoesters, polycarbonates, polyamides, polyanhydrides, polyurethanes, polyesteramides, polyphosphazenes, polyhydroxybutyrylates, polyhydroxyvalerates, polyalkylene oxalates, and copolymers, terpolymers, and mixtures thereof.

12. Any of claims 1, 2, 7, 8 or 9, wherein the thermoplastic polymer is a copolymer of glycolide, caprolactone or a lactide, or a copolymer of D,L-lactide and malolactonic acid.

13. Any of claims 1, 2, 7, 8 or 9, wherein the thermoplastic polymer is biodegradable, bioerodable or both.

14. Any of claims 1, 2, 7, 8 or 9, wherein the organic solvent is selected from the group consisting of N-methyl-2-pyrrolidone, 2-pyrrolidone, aliphatic alcohols having from two to eight carbon atoms, propylene glycol, glycerol, tetraglycol, glycerol formal, solketal, ethyl acetate, ethyl lactate, ethyl butyrate, dibutyl malonate, tributyl citrate, tri-n-hexyl acetylcitrate, diethyl succinate, diethyl glutarate, diethyl malonate, triethyl citrate, triacetin, tributyrin, diethyl carbonate, propylene carbonate, acetone, methyl ethyl ketone, dimethylacetamide, dimethylformamide, caprolactam, dimethyl sulfoxide, dimethyl sulfone, tetrahydrofuran, caprolactam, decylmethylsulfoxide, oleic acid, N,N-diethyl-m-toluamide, and 1-

dodecylazacycloheptan-2-one, 1,3-dimethyl-3,4,5,6-tetrahydro-2(1H)-pyrimidinone, and mixtures thereof.

15. A liquid delivery composition suitable for the formation of a controlled release implant, the composition comprising: a liquid, biocompatible prepolymer having at least one polymerizable ethylenically unsaturated group, and a controlled release component which includes an active agent.

16. The liquid prepolymer composition of claim 15, further comprising a curing agent.

17. The liquid prepolymer composition of claim 15, wherein the polymerizable ethylenically unsaturated group is an α,β -unsaturated carbonyl group.

18. The liquid prepolymer composition of claim 15, wherein the liquid, biocompatible prepolymer is an acrylic-ester-terminated prepolymer.

19. The liquid prepolymer composition of claim 15, further comprising a biocompatible organic solvent which is miscible or dispersible in an aqueous medium.

20. Any of claims 1, 7, 8, 9 or 15, wherein the controlled release component is a microstructure, macrostructure, low water-solubility salt of the active agent, conjugate of the active agent covalently bonded to a carrier molecule, complex of the active agent and a carrier molecule, or complex of the active agent, a carrier molecule and a metal cation.

21. Any of claims 1, 2, 7, 8, 9 or 15, wherein the controlled release component is selected from the group consisting of a microcapsule, microparticle,

nanoparticle, a cyclodextrin, liposome, micelle, fiber, film, rod, disc, and a cylinder.

22. Any of claims 1, 2, 7, 8, 9 or 15, wherein the active agent is a bioactive agent or diagnostic agent.

23. Any of claims 1, 2, 7, 8, 9 or 15, wherein the active agent is selected from the group consisting of an antibacterial agent, an antifungal agent, an antiviral agent, an anti-inflammatory agent, an antiparasitic agent, anti-neoplastic agent, an analgesic agent, an anesthetic agent, an antipsychotic agent, a vaccine, a central nervous system agent, a growth factor, a hormone, an antihistamine, an osteoinductive agent, a cardiovascular agent, an anti-ulcer agent, a bronchodilating agent, a vasodilating agent, a birth control agent, an antihypertensive agent, an anticoagulant, an antispasmodic agent, and a fertility-enhancing agent.

24. Any of claims 1, 2, 7, 8, 9 or 15, wherein the liquid delivery composition further comprises a physiologically-acceptable, release rate modification agent, a pore-forming agent, or both.

25. Use of the liquid delivery composition of any of claims 1, 2 or 15 for the manufacture of a medicament for forming a controlled release implant for delivering an active agent to a subject.

26. A method for forming a microporous, sustained release implant in situ in or on an implant site in a subject, comprising: administering the liquid delivery composition of any of claims 1, 2 or 15 to the implant site, and allowing the composition to form a solid implant with the controlled release component embedded therein.

27. A method of delivering an active agent to a subject, comprising: administering the liquid delivery composition of any of claims 1, 2 or 15 to an implant site of the subject; wherein a solid microporous, controlled release implant is formed with the controlled release component embedded therein.
28. The method of claims 26 or 27, wherein the liquid delivery composition is dispensed onto a tissue to form a film, and the composition solidifies to form a film dressing on the tissue.
29. The method of claims 26, 27 or 28, wherein the liquid delivery composition is dispensed by spraying, painting or squirting the composition onto the implant site.
30. A method of delivering an active agent to a subject, comprising: inserting into an implant site of the subject, a microporous, sustained release implant which is formed outside the subject by contacting the liquid delivery composition of claims 1 or 2 with an aqueous medium.

1 / 3






FIG. 1

2 / 3

FIG. 2



3 / 3



INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 95/03792

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 A61K9/22 A61K47/48

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US,A,4 721 613 (URQUHART ET AL.) 26 January 1988	1,13,14, 20-23
Y	see column 1, line 13 - line 20	4,5,7, 12,16, 24-30
	see column 5, line 25 - line 48	
X	WO,A,85 02092 (BIO-MIMETICS INC.) 23 May 1985	1,6,13, 14
Y	see page 55, line 13 - line 22	8
X	US,A,5 176 907 (LEONG) 5 January 1993	2,10,11
	see column 14 - column 15; examples 12,14,15	
X	GB,A,2 017 113 (JAPAN ATOMIC ENERGY RESEARCH INSTITUTE) 3 October 1979	15,17,18
Y	see page 4, line 38 - line 54	16
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

18 July 1995

Date of mailing of the international search report

26.07.95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Benz, K

INTERNATIONAL SEARCH REPORT

Internat. I Application No
PCT/US 95/03792

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP,A,0 539 751 (ATRIX LABORATORIES, INC.) 5 May 1993 cited in the application see the whole document ----	4,5,7,8, 12,16, 24-30
T	EP,A,0 649 662 (ATRIX LABORATORIES, INC.) 26 April 1995 see the whole document ----	9
A	EP,A,0 586 838 (TANABE SEIYAKU CO., LTD.) 16 March 1994 see the whole document -----	1

Form PCT/ISA/218 (continuation of second sheet) (July 1993)

INTERNATIONAL SEARCH REPORT

1 national application No.

PCT/US95/03792

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☒ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
Remark: Although claims 26-30 are directed to a method of treatment of the human/animal body the search has been carried out and based on the alleged effects of the composition.
2. ☐ Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT
Information on patent family members

Internat'l Application No
PCT/US 95/03792

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-4721613	26-01-88	US-A- 4863744	05-09-89
		US-A- 4851231	25-07-89
WO-A-8502092	23-05-85	AU-B- 565354	10-09-87
		AU-A- 3618484	03-06-85
		DE-A- 3485995	07-01-93
		EP-A, B 0163696	11-12-85
		EP-A- 0501523	02-09-92
		JP-T- 61500612	03-04-86
		US-A- 4983392	08-01-91
		US-A- 5225196	06-07-93
		US-A- 4615697	07-10-86
		US-A- 4795436	03-01-89
US-A-5176907	05-01-93	WO-A- 9303739	04-03-93
GB-A-2017113	03-10-79	JP-A- 54119585	17-09-79
		JP-C- 1181936	09-12-83
		JP-A- 54143490	08-11-79
		JP-B- 58008402	16-02-83
		JP-C- 1072859	30-11-81
		JP-A- 55033412	08-03-80
		JP-B- 56012610	23-03-81
		JP-C- 1090687	31-03-82
		JP-A- 55033425	08-03-80
		JP-B- 56032295	27-07-81
		CA-A- 1125698	15-06-82
		DE-A- 2908794	13-09-79
		FR-A- 2419299	05-10-79
		NL-A- 7901919	11-09-79
		SE-A- 7902166	10-09-79
		US-A- 4321117	23-03-82
		US-A- 4411754	25-10-83
EP-A-0539751	05-05-93	US-A- 5324519	28-06-94
		AU-A- 2605492	29-04-93
		CA-A- 2079831	29-04-93
		JP-A- 5305135	19-11-93
EP-A-0649662	26-04-95	AU-B- 6614294	13-04-95

INTERNATIONAL SEARCH REPORT

Information on patent family members

Internati Application No

PCT/US 95/03792

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0649662		CA-A- 2117394	29-03-95
EP-A-0586838	16-03-94	JP-A- 6032732	08-02-94
		CA-A- 2099941	17-01-94